



# TILEFAST

## SUPERIOR

**COST EFFECTIVE • POLYMER MODIFIED • HIGH BOND STRENGTH**

**Tilefast Superior** is an off white adhesive composed of cement, fine graded sands and other special additives. This adhesive has been polymer modified to achieve a high bond strength with non-porous tiles.

### SUITABLE SUBSTRATES

- Concrete/Cement Render
- Brickwork/Blockwork (Cement Rendered)
- Over Morgan Waterproof Membrane

INTERIOR/EXTERIOR	SUITABLE TILES
Walls	Natural Stone
Floors	Bicottura
COLOUR	Monocottura
Off White	Fully Vitrified

### PRECAUTIONS

Tilefast Superior is unsuitable for:

- bonding moisture sensitive green marble
- bonding to MDF board or timber & wax impregnated wood
- bonding to substrates subject to constant water immersion such as swimming pools

### SUBSTRATE PREPARATION & EXPANSION JOINTS

All substrates to be tiled must be flat and true, free from oil, dirt, grease or any other contaminants. Very porous substrates should be primed with **Morgan Universal Primer**. Incorporate expansion joints in accordance with AS 3958.1

**Concrete:** New concrete must be allowed to cure for 6 weeks and should have a wood float finish. Use Floor Prep to acid etch an adhesive key into concrete finished with a steel float.

**Cement Render:** Render to be left with a wood float finish and allowed to cure for 7 days.

### MIXING & POT LIFE

Add **Tilefast Superior** to clean water at a ratio of 20kg to 5 litres of water. Mix the adhesive to a smooth paste free from lumps by using a drill that has a speed lower than 300 rpm, or mix by hand. Slacken the adhesive and re-mix after 5 minutes. **Tilefast Superior** has a pot life of approximately 3 hours at 23°C and 50% relative humidity.

### OPEN TIME

**Tilefast Superior** has an open time of approximately 30 minutes, which can be shortened to just a few minutes by the action of sun, wind, high temperatures or highly absorbent surfaces. Dampening or priming the substrate prior to tiling prolongs the open time of the adhesive. Tilers need to constantly check that the adhesive has not formed a surface skin and is still fresh to touch. Adhesive with a surface skin must be always removed and discarded.

### APPLICATION, TOOLS AND ADJUSTABILITY TIME

Always install the tiles in accordance with AS 3958 1 and ensure the backs of the tiles are free of dust. Spread **Tilefast Superior** evenly across one square metre at a time with a 6mm notched trowel for walls and a 10mm notched trowel for floors. The choice of trowel should be governed by the depth of the knobs, grooves or ridges on the back of each tile and the

# TILEFAST SUPERIOR

**FREE TECHNICAL ADVICE  
& MATERIAL SAFETY DATA SHEETS**

**Email: [info@morganadhesives.com.au](mailto:info@morganadhesives.com.au)**

**Helpline: (08) 9441 6677 Response within 24 hrs**

## **COST EFFECTIVE • POLYMER MODIFIED • HIGH BOND STRENGTH**

evenness of the substrate. Lay the tiles with a fair pressure and at right angles to the adhesive notched pattern. The final bed of adhesive should be between 2mm and 4mm. Wall tiles should have a finished joint width of 2mm - 4mm and floor tiles should have a finished joint width of 3mm - 6mm. Tiles can be adjusted for approximately 30 minutes after laying.

### **COVERAGE**

20kgs of **Tilefast Superior** will cover approximately 9 square metres with a 6mm notched trowel for walls and approximately 6 square metres with a 10mm notched trowel for floors.

### **CURE TIME**

**Tilefast Superior** cures in approximately 24 hours at 23°C and 50% relative humidity. High density substrates or tiles and temperatures during installation below 10°C will significantly increase the cure time.

### **CLEAN UP**

Remove excess **Tilefast Superior** from the grout joints after 30 minutes and clean the tiles with a damp cloth or sponge. Tools and hands can be cleaned with water while the adhesive is still wet.

### **JOINT GROUTING**

Depending on environmental conditions, commence grouting after approximately 12 hours. Use **Regular** or **Superior Grout** for grout joints between 3mm to 6mm. **Morgan Slate & Quarry Grout** should be used for joint sizes between 6mm to 20mm. Use **Aquapoxy**, a three component acid resistant epoxy grout, if the joints are required to have a good chemical resistance. **Grout Add** may also be mixed with **Regular Grout** to impart extra flexibility, reduce porosity and increase water resistance.

### **JOINT GROUTING PRECAUTIONS**

**DO NOT** use excessive amounts of water during mixing or initial cleaning as this will cause irregular color finishes and also weaken the grout. **DO NOT** mix the grout with an electric drill above 300 RPM as this can entrap air into the mix causing grout to dry soft and powdery or with unsightly pin holes in the surface. **All grouts should be Damp Cured for 48 hours.** Refer to the Australian Standard AS 3958 Part 1 2007 Section 5.7.3.

### **SHELF LIFE**

Twelve months if stored in a dry & elevated position in the original factory sealed packaging.

### **PACKAGING**

**Tilefast Superior** is available in 20kg bags.

### **SPECIFICATION CLAUSE**

The wall & floor adhesive shall be Morgan **Tilefast Superior** - a tile adhesive complying with all relevant Australian technical standards.

### **MORGAN QUALITY POLICY STATEMENT**

**Tilefast Superior** is manufactured and distributed to a quality system based on ISO 9001:2000. **Tilefast Superior** is guaranteed for 25 years when installed to the guidelines of AS 3958 Part 1 & 2, 2007 and in conjunction with written technical information supplied by **Morgan Ceramic Tile Adhesives**.

**USER NOTE** Although the technical details and recommendations contained in this brochure correspond to the best of our knowledge and experience, all of the above information must, in every case, be taken as merely indicative and subject to confirmation after long term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in any case the user is fully responsible for all consequences deriving from the use of the product.



24 Hanwell Way, Bassendean WA 6054  
Ph: 08 9279 8911 • Fx: 08 6278 1152

[www.morganadhesives.com.au](http://www.morganadhesives.com.au)